

PRODUCT DATA SHEET

Sika® Separol®-30 D Mineral New

DEFERRED MOULD RELEASE AGENT - MINERAL NEW

DESCRIPTION

Sika® Separol®-30 D Mineral New is a mineral new mould release agent ready to use.

USES

Sika® Separol®-30 D Mineral New can be used like a deferred mould release agent for jobsite :

- On steel, wood, polyurethane, polyester
- With cold or warm conditions, just at a formwork temperature of 70°C.

CHARACTERISTICS / ADVANTAGES

- For deferred release
- Usable when ambient temperature and/or formwork temperature are below 0°C until 70°C
- Extend the formwork useful life
- Delete the adhesion of the concrete and of the concrete laitance on the treated area
- Allow the later application of coating or paint (the validation of the support is the responsibility of the applicator).

PRODUCT INFORMATION

| | |
|------------------------------|--|
| Packaging | <ul style="list-style-type: none"> ▪ 20 liters cans ▪ 210 liters drums ▪ 1000 liters IBC ▪ Bulk |
| Shelf life | 3 years from date of production if stored properly in original unopened packaging. |
| Storage conditions | <ul style="list-style-type: none"> ▪ Stored between -15 and +35°C ▪ Comply with the Safety Data Sheet |
| Appearance and colour | Light brown |
| Density | ≈ 0.84 at 20°C |
| Consumption | <ul style="list-style-type: none"> ▪ Steel formwork or smooth wood : 50 to 80 m²/liter ▪ More absorbent formwork : 25 to 35 m²/liter |

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

APPLICATION

This mould release agent can be apply with :

- A brush
- A roller
- A spraying machine with a minimum pressure of 3 bars.

Sika® Separol®-30 D Mineral New must not be diluted. The application of the oil must be uniform because an excess will tend to run down on vertical surfaces. Remove excess of oil using a dry cloth or sponge.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Chemicals Ghana Ltd

Kpone Rd, Kpone Katamanso
GK-0028-7646 Greater Accra, Ghana
Mobile: +233 025 795 9292
Web: gha.sika.com

PRODUCT DATA SHEET

Sika® Separol®-30 D Mineral New
February 2023, Version 02.01
021405021000000342

SikaSeparol-30DMineralNew-en-GH-(02-2023)-2-1.pdf