

## PRODUCT DATA SHEET

Sika Boom<sup>®</sup> P

## EXPANSIVE POLYURETHANE FIXING FOAM FOR FILLING AND INSULATING

## DESCRIPTION

Sika Boom<sup>®</sup> P is a 1-component, fast curing polyurethane foam made for easy application with plastic nozzle

## USES

Sika Boom<sup>®</sup> P is designed for fixing, insulating and filling connection joints around windows and door frames, pipe entries, air-conditioning vents and electrical equipment. Sika Boom<sup>®</sup> S allows insulation against noise, cold and draughts after a single application

## CHARACTERISTICS / ADVANTAGES

- 1-Component
- Easy application with nozzle
- High expanding rate
- Fast curing
- Very good thermal insulation
- Effective sound dampening
- HFC-free

## PRODUCT INFORMATION

Composition	Polyurethane
Packaging	Sika Boom <sup>®</sup> P shall be stored in an upright position, in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.
Colour	Light yellow
Shelf life	Sika Boom <sup>®</sup> P has a shelf life of 15 months from the date of production, if stored properly in undamaged, original, sealed packaging, and if the storage conditions are met. Opened cans of Sika Boom <sup>®</sup> P must be used within 4 weeks
Storage conditions	Sika Boom <sup>®</sup> P shall be stored in an upright position, in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.
Density	0,022 ± 3 kg/dm <sup>3</sup>

## TECHNICAL INFORMATION

Compressive strength	0,03 MPa
Dimensional stability	± 10%.
Resistance to fire	B3
Temperature resistance	Aprox. 0,036 W/mK.
Water absorption	Max. 1% volume

## APPLICATION INFORMATION

Consumption	Max. aprox. 45 dm <sup>3</sup>
Ambient air temperature	+10 °C min. / +30 °C max.
Relative air humidity	30 % min. / 95 % max.
Substrate temperature	+10 °C min. / +30 °C max.
Curing time	Sika Boom® P is fully cured after 12 h
Cutting time	Aprox. 30 minutes
Tack free time	5 to 10 minutes

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

Safety Data Sheet

## IMPORTANT CONSIDERATIONS

- The minimum can temperature for application must be +10 °C.
- In order to get a good quality foam, the can temperature should not vary more than 10 °C from the ambient temperature.
- Protect the can from direct sunlight and temperatures above +50 °C (danger of explosion).
- For correct curing of the foam, moisture is necessary.
- Applying insufficient moisture may lead to subsequent unintended foam expansion (post expansion).
- Do not fill hollow sections completely as the foam expands during curing.
- Do not use on polyethylene (PE), polypropylene (PP), polytetrafluoroethylene (PTFE / Teflon), and silicone, oil, grease and other separating agents.
- Sika Boom® P is not resistant to UV light.
- Read all safety and technical recommendations which are printed on the Sika Boom® P can.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

For the application of Sika Boom® P all generally accepted rules of building and construction apply.

### SUBSTRATE PREPARATION

The substrate must be clean, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed. Sika Boom® P adheres without primers and/or activators. Pre-dampen the substrate with clean water, this ensures that the foam cures properly and also prevents secondary foam expansion.

## CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately with Sika Boom®-Cleaner and/or Sika® Remover-208. Once cured, residual material can only be removed mechanically.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Chemicals Ghana Ltd

Kpone Rd, Kpone Katamanso  
GK-0028-7646 Greater Accra, Ghana  
Mobile: +233 025 795 9292  
Web: gha.sika.com

### PRODUCT DATA SHEET

Sika Boom® P  
October 2022, Version 01.01  
02051406000000032

SikaBoomP-en-GH-(10-2022)-1-1.pdf